

pvap	8.99e-03	kPa	408.15	Temperature-Dependent Vapor Pressure of Selected Cyclic and Linear Polydimethylsiloxane Oligomers
pvap	0.02	kPa	418.15	Temperature-Dependent Vapor Pressure of Selected Cyclic and Linear Polydimethylsiloxane Oligomers
pvap	0.05	kPa	428.15	Temperature-Dependent Vapor Pressure of Selected Cyclic and Linear Polydimethylsiloxane Oligomers
pvap	0.10	kPa	438.15	Temperature-Dependent Vapor Pressure of Selected Cyclic and Linear Polydimethylsiloxane Oligomers

Sources

Crippen Method:

https://www.chemeo.com/doc/models/crippen_log10ws

Temperature-Dependent Vapor Pressure of Selected Cyclic and Linear Polydimethylsiloxane Oligomers:

<https://www.doi.org/10.1021/je100835n>

<http://pubs.acs.org/doi/abs/10.1021/ci990307i>

Legend

log10ws: Log10 of Water solubility in mol/l
logp: Octanol/Water partition coefficient
pvap: Vapor pressure

Latest version available from:

<https://www.chemeo.com/cid/104-794-5/tetracosamethylundecasiloxane.pdf>

Generated by Cheméo on 2024-04-18 23:34:20.954599214 +0000 UTC m=+15772509.875176525.

Cheméo (<https://www.chemeo.com>) is the biggest free database of chemical and physical data for the process industry.