

zinc

Inchi:	InChI=1S/Zn
InchiKey:	HCHKCACWOHOZIP-UHFFFAOYSA-N
Formula:	Zn
SMILES:	[Zn]
Mol. weight [g/mol]:	65.38
CAS:	7440-66-6

Physical Properties

Property code	Value	Unit	Source
affp	608.60	kJ/mol	NIST Webbook
basg	586.00	kJ/mol	NIST Webbook
hf	130.40 ± 0.40	kJ/mol	NIST Webbook
ie	9.39 ± 0.00	eV	NIST Webbook
ie	9.57 ± 0.07	eV	NIST Webbook
ie	9.39	eV	NIST Webbook
ie	9.39	eV	NIST Webbook
ie	9.39	eV	NIST Webbook
ie	9.39	eV	NIST Webbook
ie	9.39	eV	NIST Webbook
sgb	160.99 ± 0.00	J/mol×K	NIST Webbook
ss	41.63 ± 0.15	J/mol×K	NIST Webbook
tf	692.65 ± 0.10	K	NIST Webbook
tf	692.83 ± 0.30	K	NIST Webbook
tf	965.74 ± 0.05	K	NIST Webbook

Correlations

Information	Value
Property code	pvap
Equation	$\ln(P_{vp}) = A + B/(T + C)$
Coeff. A	1.54250e+01
Coeff. B	-1.20684e+04
Coeff. C	-6.97600e+01
Temperature range (K), min.	610.15

Sources

Thermophysical properties of the liquid Ga-Sn-Zn eutectic alloy:	https://www.doi.org/10.1016/j.fluid.2018.03.001
Mixing enthalpy of liquid Ga Li Zn alloys:	https://www.doi.org/10.1016/j.tca.2015.12.011
The measurement of thermal conductivity variation with temperature for the vapor based pressure of ternary solders:	https://www.doi.org/10.1016/j.tca.2012.12.012
The Yaws Handbook of Vapor based Pressure:	https://www.sciencedirect.com/book/9780128029992/the-yaws-handbook-of-vapor-pressure
Thermal conductivities of solid and liquid phases in Pb Cd and Sn Zn	https://www.doi.org/10.1016/j.tca.2007.01.009
Synthesis, characterization and standard molar enthalpies of formation of In-Zn-Sn system:	https://www.doi.org/10.1016/j.jct.2019.07.010
Direct reaction method and Measurement of zinc activity in the ternary In Zn Sn alloys by EMFmethod:	https://www.doi.org/10.1016/j.jct.2016.03.017
Thermodynamic properties of Ga-Zn system. Experiment vs model:	https://www.doi.org/10.1016/j.tca.2013.06.039
Vaporization in the Ga₂O₃-ZnO system by high temperature mass spectrometry, and thermodynamic investigation of zinc and cadmium	https://www.doi.org/10.1016/j.jct.2016.07.029
Thermophysical properties of Ga-Zn eutectic alloys with Sn additions:	https://www.doi.org/10.1016/j.jct.2017.07.009
Calorimetric method for determining the thermochemical energy storage capacities of redox metal oxides:	https://www.doi.org/10.1016/j.jct.2017.07.020
Enthalpies of Mixing of Liquid In-Sn and In-Sn-Zn Alloys:	https://www.doi.org/10.1016/j.fluid.2018.07.008
The physicochemical properties of liquid Ga-Zn alloys:	https://www.doi.org/10.1016/j.tca.2019.01.008
Vaporization thermodynamics of the ZnO-SnO₂ system:	https://www.doi.org/10.1016/j.fluid.2010.02.008
Variations of thermal conductivity with temperature and composition of Zn in the Bi_xZn_{1-x} Zn 2 at.% Al alloys:	https://www.doi.org/10.1016/j.tca.2013.03.025
Thermodynamic description of the Ga-Li-Zn system:	https://www.doi.org/10.1016/j.jct.2013.11.010
Thermal conductivity and interfacial energy of solid Bi solution in the Ga-Li-Zn system:	https://www.doi.org/10.1016/j.fluid.2012.07.033
Calorimetric measurements of liquid (Al + Li + Zn) alloys:	http://webbook.nist.gov/cgi/cbook.cgi?ID=C7440666&Units=SI
Thermodynamic description of the Ga-Li-Zn system:	https://www.doi.org/10.1016/j.tca.2017.10.004
Thermal conductivity and interfacial energy of solid Bi solution in the Ga-Li-Zn system:	https://www.doi.org/10.1016/j.fluid.2010.02.029
Calorimetric measurements of liquid (Al + Li + Zn) alloys:	https://www.doi.org/10.1016/j.jct.2015.09.008

Legend

affp:	Proton affinity
basg:	Gas basicity
hf:	Enthalpy of formation at standard conditions
ie:	Ionization energy
pvap:	Vapor pressure
sgb:	Molar entropy at standard conditions (1 bar)
ss:	Solid phase molar entropy at standard conditions
tf:	Normal melting (fusion) point

Latest version available from:

<https://www.chemeo.com/cid/19-712-0/zinc.pdf>

Generated by Cheméo on 2024-03-13 06:50:46.291525231 +0000 UTC m=+12601895.212102565.

Cheméo (<https://www.chemeo.com>) is the biggest free database of chemical and physical data for the process industry.