

Benzenamine, 4,4'-oxybis-

Other names:	4,4'-Diaminobiphenyl oxide 4,4'-Diaminodiphenyl oxide 4,4'-Diaminophenyl ether 4,4'-Diaminophenyl oxide 4,4'-Oxybis[aniline] 4,4'-Oxybisbenzenamine 4,4'-Oxydiphenylamine 4,4'-diaminodiphenyl ether 4,4'-oxydianiline 4,4-Dadpe 4,4-Diaminodiphenyl ether 4,4-Oxydianiline 4-(4-Aminophenoxy)phenylamine 4-aminophenyl ether Aniline, 4,4'-oxydi- Bis(p-aminophenyl) ether Dadpe Diaminodiphenyl ether Ether, 4,4'-diaminodiphenyl- NCI-C50146 NSC 37075 Oxybis[4-aminobenzene] Oxydi-p-phenylenediamine Oxydianiline bis(4-aminophenyl) ether di(4-Aminophenyl) ether p,p'-Diaminodiphenyl ether p,p'-Oxybis(aniline) p,p'-Oxydianiline p-Aminophenyl ether
Inchi:	InChI=1S/C12H12N2O/c13-9-1-5-11(6-2-9)15-12-7-3-10(14)4-8-12/h1-8H,13-14H2
InchiKey:	HLBLWEWZXPIGSM-UHFFFAOYSA-N
Formula:	C12H12N2O
SMILES:	<chem>Nc1ccc(Oc2ccc(N)cc2)cc1</chem>
Mol. weight [g/mol]:	200.24
CAS:	101-80-4

Physical Properties

Property code	Value	Unit	Source
chs	-6420.00 ± 1.00	kJ/mol	NIST Webbook
gf	283.62	kJ/mol	Joback Method
hf	94.47	kJ/mol	Joback Method
hfs	-17.00	kJ/mol	NIST Webbook
hfus	25.72	kJ/mol	Joback Method
hvap	71.87	kJ/mol	Joback Method
ie	6.55	eV	NIST Webbook
log10ws	-2.37		Crippen Method
logp	2.643		Crippen Method
mcvol	158.250	ml/mol	McGowan Method
pc	3713.49	kPa	Joback Method
ss	241.00	J/mol×K	NIST Webbook
tb	704.76	K	Joback Method
tc	965.17	K	Joback Method
tf	462.67	K	Measurement and correlation of the solubility of 4,4'-oxydianiline in different organic solvents
tf	464.00	K	NIST Webbook
tf	465.40 ± 0.10	K	NIST Webbook
vc	0.568	m ³ /kmol	Joback Method

Temperature Dependent Properties

Property code	Value	Unit	Temperature [K]	Source
cpg	479.82	J/mol×K	965.17	Joback Method
cpg	428.71	J/mol×K	748.16	Joback Method
cpg	441.06	J/mol×K	791.56	Joback Method
cpg	452.30	J/mol×K	834.96	Joback Method
cpg	462.47	J/mol×K	878.37	Joback Method
cpg	471.63	J/mol×K	921.77	Joback Method
cpg	415.20	J/mol×K	704.76	Joback Method
cps	278.20	J/mol×K	298.00	NIST Webbook
cps	280.70	J/mol×K	298.00	NIST Webbook
cps	258.40	J/mol×K	300.00	NIST Webbook
hfust	7.74	kJ/mol	465.40	NIST Webbook
hfust	7.74	kJ/mol	465.40	NIST Webbook

Sources

NIST Webbook:	http://webbook.nist.gov/cgi/cbook.cgi?ID=C101804&Units=SI
Crippen Method:	http://pubs.acs.org/doi/abs/10.1021/ci990307l
Crippen Method:	https://www.chemeo.com/doc/models/crippen_log10ws
Measurement and correlation of the solubility of 4,4'-oxydianiline in methylene chloride:	https://www.doi.org/10.1016/j.fluid.2013.07.010
Measurement and correlation of the solubilities of aromatic polyimide monomers in supercritical carbon dioxide with acetone:	https://www.doi.org/10.1016/j.jct.2012.04.013
Joback Method:	https://en.wikipedia.org/wiki/Joback_method
McGowan Method:	http://link.springer.com/article/10.1007/BF02311772

Legend

chs:	Standard solid enthalpy of combustion
cpg:	Ideal gas heat capacity
cps:	Solid phase heat capacity
gf:	Standard Gibbs free energy of formation
hf:	Enthalpy of formation at standard conditions
hfs:	Solid phase enthalpy of formation at standard conditions
hfus:	Enthalpy of fusion at standard conditions
hfust:	Enthalpy of fusion at a given temperature
hvap:	Enthalpy of vaporization at standard conditions
ie:	Ionization energy
log10ws:	Log10 of Water solubility in mol/l
logp:	Octanol/Water partition coefficient
mcvol:	McGowan's characteristic volume
pc:	Critical Pressure
sfust:	Entropy of fusion at a given temperature
ss:	Solid phase molar entropy at standard conditions
tb:	Normal Boiling Point Temperature
tc:	Critical Temperature
tf:	Normal melting (fusion) point
vc:	Critical Volume

Latest version available from:

<https://www.chemeo.com/cid/26-993-1/Benzenamine-4-4-oxybis.pdf>

Generated by Cheméo on 2024-04-09 07:45:04.529501492 +0000 UTC m=+14937953.450078807.

Cheméo (<https://www.chemeo.com>) is the biggest free database of chemical and physical data for the process industry.