

uranium

Inchi:

InChI=1S/U

InchiKey:

JFALSRLKYAFGM-UHFFFAOYSA-N

Formula:

U

SMILES:

[U]

Mol. weight [g/mol]:

238.03

CAS:

7440-61-1

Physical Properties

Property code	Value	Unit	Source
affp	995.20	kJ/mol	NIST Webbook
basg	973.20	kJ/mol	NIST Webbook
hf	533.00 ± 8.00	kJ/mol	NIST Webbook
ie	6.22 ± 0.02	eV	NIST Webbook
ie	6.00 ± 0.30	eV	NIST Webbook
ie	6.09 ± 0.11	eV	NIST Webbook
ie	6.00 ± 0.50	eV	NIST Webbook
ie	6.00 ± 0.50	eV	NIST Webbook
ie	6.19 ± 0.00	eV	NIST Webbook
ie	6.19 ± 0.00	eV	NIST Webbook
ie	6.05 ± 0.07	eV	NIST Webbook
ie	6.10 ± 0.10	eV	NIST Webbook
ie	6.05 ± 0.07	eV	NIST Webbook
ie	6.19	eV	NIST Webbook
ie	6.80 ± 1.50	eV	NIST Webbook
ie	6.20 ± 0.50	eV	NIST Webbook
ie	6.19 ± 0.06	eV	NIST Webbook
ie	6.10 ± 0.30	eV	NIST Webbook
ie	6.00 ± 0.50	eV	NIST Webbook
ie	6.19 ± 0.06	eV	NIST Webbook
ie	6.11 ± 0.05	eV	NIST Webbook
ie	6.08 ± 0.08	eV	NIST Webbook
ie	6.19	eV	NIST Webbook
ie	6.30 ± 0.30	eV	NIST Webbook
sgb	199.79 ± 0.10	J/mol×K	NIST Webbook
ss	50.20 ± 0.20	J/mol×K	NIST Webbook

Correlations

Information	Value
Property code	pvap
Equation	$\ln(P_{vp}) = A + B/(T + C)$
Coeff. A	1.58761e+01
Coeff. B	-5.35877e+04
Coeff. C	3.26850e+02
Temperature range (K), min.	2325.15
Temperature range (K), max.	4402.15

Sources

Thermodynamic properties and behaviour of A2[(UO2)(MoO4)2] compounds with a thermodynamic investigation of A2[(UO2)2(MoO4)O2] compounds with a thermodynamic investigation of potassium uranyl oxalate K2(UO2)2(C2O4)·6H2O: A2[(UO2)2(WO5)O] compounds with A

Thermodynamic and calculated phase diagrams for the K2O-UO3-U2O5 system. An experimental calorimetric and a DFT + U study of the thermodynamic properties of

The Yaws Handbook of Vapor Pressure

Pressure of (UO2)4(WO5)(W2O8)O2] and (Ga+Sn) eutectic alloy:

A calorimetric and thermodynamic investigation of cesium uranyl trioxalate Cs3[(UO2)(WO4)3(WO3)2] compound:

Thermodynamic investigation of Na2U2O7 using Knudsen effusion mass spectrometry and variation of Gibbs energy of formation of RE2UO12 (RE = La, Nd, Sm, Eu, Gd, Tb, Dy, Ho, Tm, Yb, Lu) along the 4f series:

<https://www.doi.org/10.1016/j.jct.2014.07.009>

<https://www.doi.org/10.1016/j.jct.2015.06.028>

<https://www.doi.org/10.1016/j.jct.2012.09.014>

<https://www.doi.org/10.1016/j.jct.2017.03.039>

<https://www.doi.org/10.1016/j.jct.2018.10.014>

<https://www.doi.org/10.1016/j.jct.2019.07.015>

<https://www.sciencedirect.com/book/9780128029992/the-yaws-handbook-of-vapor-pressure>

<https://www.doi.org/10.1016/j.jct.2015.09.023>

<https://www.doi.org/10.1016/j.jct.2019.05.012>

<https://www.doi.org/10.1016/j.tca.2016.05.012>

<https://www.doi.org/10.1016/j.jct.2015.06.026>

<https://www.doi.org/10.1016/j.jct.2019.06.030>

<http://webbook.nist.gov/cgi/cbook.cgi?ID=C7440611&Units=SI>

Legend

- affp:** Proton affinity

basg: Gas basicity

hf: Enthalpy of formation at standard conditions

ie: Ionization energy

pvap: Vapor pressure

sgb: Molar entropy at standard conditions (1 bar)

ss: Solid phase molar entropy at standard conditions

Latest version available from:

<https://www.chemeo.com/cid/42-027-5/uranium.pdf>

Generated by Cheméo on 2025-12-05 14:01:51.289570995 +0000 UTC m=+4691508.819611659.

Cheméo (<https://www.chemeo.com>) is the biggest free database of chemical and physical data for the process industry.