

# Methyl methacrylate

<b>Other names:</b>	2-(Methoxycarbonyl)-1-propene 2-Methyl-2-propenoic acid methyl ester 2-Methylacrylic acid, methyl ester 2-Methylacrylic, methyl ester 2-Propenoic acid, 2-methyl-, methyl ester 2-methylpropenoic acid, methyl ester Acryester M Acrylic acid, 2-methyl-, methyl ester CH <sub>2</sub> =C(CH <sub>3</sub> )COOCH <sub>3</sub> Diakon MMA Metakrylan metylu Methacrylate de methyle Methacrylic acid methyl ester Methacrylsaeuremethyl ester Methyl 2-methyl-2-propenoate Methyl 2-methylpropenoate Methyl ester of 2-methyl-2-propenoic acid Methyl methacrylate monomer Methyl methylacrylate Methyl «alpha»-methylacrylate Methyl «alpha»-methylacrylate Methyl-methacrylat Methyl-«alpha»-methacrylate Methyl-«alpha»-methacrylate Methylester kyseliny methakrylove Methylmethacrylaat Metil metacrilato Monocite methacrylate monomer NCI-C50680 NSC 4769 Paladon Pegalan Rcra waste number U162 TEB 3K methacrylic acid, methyl ester
<b>Inchi:</b>	InChI=1S/C5H8O2/c1-4(2)5(6)7-3/h1H2,2-3H3
<b>InchiKey:</b>	VVQNEPGJFQJSBK-UHFFFAOYSA-N
<b>Formula:</b>	C <sub>5</sub> H <sub>8</sub> O <sub>2</sub>
<b>SMILES:</b>	C=C(C)C(=O)OC

Mol. weight [g/mol]: 100.12  
 CAS: 80-62-6

## Physical Properties

Property code	Value	Unit	Source
affp	831.40	kJ/mol	NIST Webbook
basg	800.50	kJ/mol	NIST Webbook
chl	-2724.60 ± 4.00	kJ/mol	NIST Webbook
gf	-163.41	kJ/mol	Joback Method
hf	-348.70	kJ/mol	NIST Webbook
hf	-331.00	kJ/mol	NIST Webbook
hf	-342.30	kJ/mol	NIST Webbook
hfl	-388.80 ± 4.00	kJ/mol	NIST Webbook
hfl	-382.40	kJ/mol	NIST Webbook
hfus	8.90	kJ/mol	Joback Method
hvap	40.10	kJ/mol	NIST Webbook
ie	10.06	eV	NIST Webbook
ie	10.28	eV	NIST Webbook
ie	9.70	eV	NIST Webbook
log10ws	-0.80		Aqueous Solubility Prediction Method
logp	0.735		Crippen Method
mcvol	84.450	ml/mol	McGowan Method
pc	3881.95	kPa	Joback Method
rinpol	699.00		NIST Webbook
rinpol	700.00		NIST Webbook
rinpol	694.00		NIST Webbook
rinpol	666.00		NIST Webbook
rinpol	670.00		NIST Webbook
rinpol	696.00		NIST Webbook
rinpol	677.00		NIST Webbook
rinpol	677.00		NIST Webbook
rinpol	677.00		NIST Webbook
rinpol	677.00		NIST Webbook
rinpol	732.00		NIST Webbook
rinpol	710.40		NIST Webbook
rinpol	723.00		NIST Webbook
rinpol	672.00		NIST Webbook
rinpol	710.00		NIST Webbook
rinpol	696.00		NIST Webbook

rinpol	714.00		NIST Webbook
rinpol	699.00		NIST Webbook
rinpol	696.00		NIST Webbook
rinpol	696.00		NIST Webbook
rinpol	699.00		NIST Webbook
rinpol	677.00		NIST Webbook
rinpol	713.44		NIST Webbook
rinpol	677.00		NIST Webbook
rinpol	732.00		NIST Webbook
rinpol	717.33		NIST Webbook
rinpol	714.30		NIST Webbook
rinpol	699.00		NIST Webbook
rinpol	716.28		NIST Webbook
ripol	1008.00		NIST Webbook
ripol	1002.00		NIST Webbook
ripol	1008.00		NIST Webbook
ripol	1002.00		NIST Webbook
ripol	1010.00		NIST Webbook
sl	266.20	J/molxK	NIST Webbook
tb	386.65	K	Joback Method
tc	572.77	K	Joback Method
tf	225.60	K	NIST Webbook
tf	225.60	K	NIST Webbook
tf	225.00	K	NIST Webbook
tf	225.15 ± 0.40	K	NIST Webbook
tf	225.26	K	Aqueous Solubility Prediction Method
tf	225.50 ± 0.20	K	NIST Webbook
tf	225.60 ± 0.20	K	NIST Webbook
tt	225.59 ± 0.02	K	NIST Webbook
vc	0.322	m <sup>3</sup> /kmol	Joback Method

## Temperature Dependent Properties

Property code	Value	Unit	Temperature [K]	Source
cpg	149.36	J/molxK	386.65	Joback Method
cpg	186.04	J/molxK	541.75	Joback Method
cpg	179.24	J/molxK	510.73	Joback Method
cpg	172.17	J/molxK	479.71	Joback Method
cpg	164.83	J/molxK	448.69	Joback Method
cpg	157.23	J/molxK	417.67	Joback Method

cpg	192.58	J/molxK	572.77	Joback Method
cpl	191.09	J/molxK	298.15	NIST Webbook
cpl	188.49	J/molxK	293.00	NIST Webbook
cpl	210.55	J/molxK	298.15	NIST Webbook
cpl	192.40	J/molxK	300.00	NIST Webbook
cpl	215.30	J/molxK	298.15	NIST Webbook
cpl	215.30	J/molxK	298.15	NIST Webbook
cps	150.20	J/molxK	210.00	NIST Webbook
dvisc	0.0003398	Paxs	353.15	Density, Excess Molar Volume, and Viscosity for the Methyl Methacrylate + 1-Butyl-3-methylimidazolium Hexafluorophosphate Ionic Liquid Binary System at Atmospheric Pressure
dvisc	0.0006337	Paxs	288.15	Excess Molar Volume and Viscosity Deviation for the Methanol + Methyl Methacrylate Binary System at T) (283.15 to 333.15) K
dvisc	0.0005899	Paxs	293.15	Excess Molar Volume and Viscosity Deviation for the Methanol + Methyl Methacrylate Binary System at T) (283.15 to 333.15) K
dvisc	0.0005540	Paxs	298.15	Excess Molar Volume and Viscosity Deviation for the Methanol + Methyl Methacrylate Binary System at T) (283.15 to 333.15) K
dvisc	0.0005248	Paxs	303.15	Excess Molar Volume and Viscosity Deviation for the Methanol + Methyl Methacrylate Binary System at T) (283.15 to 333.15) K

dvisc	0.0004956	Paxs	308.15	Excess Molar Volume and Viscosity Deviation for the Methanol + Methyl Methacrylate Binary System at T) (283.15 to 333.15) K
dvisc	0.0004719	Paxs	313.15	Excess Molar Volume and Viscosity Deviation for the Methanol + Methyl Methacrylate Binary System at T) (283.15 to 333.15) K
dvisc	0.0004497	Paxs	318.15	Excess Molar Volume and Viscosity Deviation for the Methanol + Methyl Methacrylate Binary System at T) (283.15 to 333.15) K
dvisc	0.0004294	Paxs	323.15	Excess Molar Volume and Viscosity Deviation for the Methanol + Methyl Methacrylate Binary System at T) (283.15 to 333.15) K
dvisc	0.0004100	Paxs	328.15	Excess Molar Volume and Viscosity Deviation for the Methanol + Methyl Methacrylate Binary System at T) (283.15 to 333.15) K
dvisc	0.0003938	Paxs	333.15	Excess Molar Volume and Viscosity Deviation for the Methanol + Methyl Methacrylate Binary System at T) (283.15 to 333.15) K

dvisc	0.0006808	Paxs	283.15	Density, Excess Molar Volume, and Viscosity for the Methyl Methacrylate + 1-Butyl-3-methylimidazolium Hexafluorophosphate Ionic Liquid Binary System at Atmospheric Pressure
dvisc	0.0006337	Paxs	288.15	Density, Excess Molar Volume, and Viscosity for the Methyl Methacrylate + 1-Butyl-3-methylimidazolium Hexafluorophosphate Ionic Liquid Binary System at Atmospheric Pressure
dvisc	0.0005899	Paxs	293.15	Density, Excess Molar Volume, and Viscosity for the Methyl Methacrylate + 1-Butyl-3-methylimidazolium Hexafluorophosphate Ionic Liquid Binary System at Atmospheric Pressure
dvisc	0.0005540	Paxs	298.15	Density, Excess Molar Volume, and Viscosity for the Methyl Methacrylate + 1-Butyl-3-methylimidazolium Hexafluorophosphate Ionic Liquid Binary System at Atmospheric Pressure
dvisc	0.0005248	Paxs	303.15	Density, Excess Molar Volume, and Viscosity for the Methyl Methacrylate + 1-Butyl-3-methylimidazolium Hexafluorophosphate Ionic Liquid Binary System at Atmospheric Pressure

dvisc	0.0004956	Paxs	308.15	Density, Excess Molar Volume, and Viscosity for the Methyl Methacrylate + 1-Butyl-3-methylimidazolium Hexafluorophosphate Ionic Liquid Binary System at Atmospheric Pressure
dvisc	0.0004719	Paxs	313.15	Density, Excess Molar Volume, and Viscosity for the Methyl Methacrylate + 1-Butyl-3-methylimidazolium Hexafluorophosphate Ionic Liquid Binary System at Atmospheric Pressure
dvisc	0.0004497	Paxs	318.15	Density, Excess Molar Volume, and Viscosity for the Methyl Methacrylate + 1-Butyl-3-methylimidazolium Hexafluorophosphate Ionic Liquid Binary System at Atmospheric Pressure
dvisc	0.0004294	Paxs	323.15	Density, Excess Molar Volume, and Viscosity for the Methyl Methacrylate + 1-Butyl-3-methylimidazolium Hexafluorophosphate Ionic Liquid Binary System at Atmospheric Pressure
dvisc	0.0004100	Paxs	328.15	Density, Excess Molar Volume, and Viscosity for the Methyl Methacrylate + 1-Butyl-3-methylimidazolium Hexafluorophosphate Ionic Liquid Binary System at Atmospheric Pressure

dvisc	0.0006808	Paxs	283.15	Excess Molar Volume and Viscosity Deviation for the Methanol + Methyl Methacrylate Binary System at T) (283.15 to 333.15) K
dvisc	0.0003636	Paxs	343.15	Density, Excess Molar Volume, and Viscosity for the Methyl Methacrylate + 1-Butyl-3-methylimidazolium Hexafluorophosphate Ionic Liquid Binary System at Atmospheric Pressure
dvisc	0.0003938	Paxs	333.15	Density, Excess Molar Volume, and Viscosity for the Methyl Methacrylate + 1-Butyl-3-methylimidazolium Hexafluorophosphate Ionic Liquid Binary System at Atmospheric Pressure
hfust	14.44	kJ/mol	225.59	NIST Webbook
hfust	12.24	kJ/mol	225.00	NIST Webbook
hfust	13.45	kJ/mol	225.50	NIST Webbook
hfust	12.24	kJ/mol	225.00	NIST Webbook
hsubt	60.70	kJ/mol	208.50	NIST Webbook
hvapt	33.30 ± 0.40	kJ/mol	340.50	NIST Webbook
hvapt	38.00	kJ/mol	339.00	NIST Webbook
hvapt	37.70	kJ/mol	333.00	NIST Webbook
hvapt	36.30 ± 0.20	kJ/mol	340.50	NIST Webbook
hvapt	39.00	kJ/mol	337.00	NIST Webbook
hvapt	37.90	kJ/mol	333.00	NIST Webbook
hvapt	38.80 ± 0.10	kJ/mol	340.50	NIST Webbook
rhol	926.16	kg/m <sup>3</sup>	308.15	Densities, ultrasonic speeds, excess and partial molar properties of binary mixtures of acetonitrile with some alkyl methacrylates at temperatures from 293.15 K to 318.15 K



rho1	931.90	kg/m3	303.15	Densities, ultrasonic speeds, excess and partial molar properties of binary mixtures of acetonitrile with some alkyl methacrylates at temperatures from 293.15 K to 318.15 K
rho1	914.67	kg/m3	318.15	Densities, ultrasonic speeds, excess and partial molar properties of binary mixtures of acetonitrile with some alkyl methacrylates at temperatures from 293.15 K to 318.15 K
rho1	937.64	kg/m3	298.15	Densities, ultrasonic speeds, excess and partial molar properties of binary mixtures of acetonitrile with some alkyl methacrylates at temperatures from 293.15 K to 318.15 K
rho1	943.38	kg/m3	293.15	Densities, ultrasonic speeds, excess and partial molar properties of binary mixtures of acetonitrile with some alkyl methacrylates at temperatures from 293.15 K to 318.15 K
rho1	914.66	kg/m3	318.15	Densities, ultrasonic speeds, viscosities and excess properties of binary mixtures of methyl methacrylate with N,N-dimethylformamide and N,N-dimethylacetamide at different temperatures

rho1	920.41	kg/m3	313.15	Densities, ultrasonic speeds, viscosities and excess properties of binary mixtures of methyl methacrylate with N,N-dimethylformamide and N,N-dimethylacetamide at different temperatures
rho1	926.15	kg/m3	308.15	Densities, ultrasonic speeds, viscosities and excess properties of binary mixtures of methyl methacrylate with N,N-dimethylformamide and N,N-dimethylacetamide at different temperatures
rho1	931.89	kg/m3	303.15	Densities, ultrasonic speeds, viscosities and excess properties of binary mixtures of methyl methacrylate with N,N-dimethylformamide and N,N-dimethylacetamide at different temperatures
rho1	937.63	kg/m3	298.15	Densities, ultrasonic speeds, viscosities and excess properties of binary mixtures of methyl methacrylate with N,N-dimethylformamide and N,N-dimethylacetamide at different temperatures

rho1	943.37	kg/m3	293.15	Densities, ultrasonic speeds, viscosities and excess properties of binary mixtures of methyl methacrylate with N,N-dimethylformamide and N,N-dimethylacetamide at different temperatures
rho1	949.10	kg/m3	288.15	Densities, ultrasonic speeds, viscosities and excess properties of binary mixtures of methyl methacrylate with N,N-dimethylformamide and N,N-dimethylacetamide at different temperatures
rho1	937.65	kg/m3	298.15	Densities and volumes of mixing of the ternary system toluene + butyl acrylate + methyl methacrylate and its binaries at 298.15 K
rho1	920.42	kg/m3	313.15	Densities, ultrasonic speeds, excess and partial molar properties of binary mixtures of acetonitrile with some alkyl methacrylates at temperatures from 293.15 K to 318.15 K
rho1	937.63	kg/m3	298.15	Volumetric Properties of 3-Methylbutyl Ethanoate with Ethyl Acrylate, Butyl Acrylate, Methyl Methacrylate, and Styrene at 25 C
sfust	59.65	J/molxK	225.50	NIST Webbook
sfust	64.00	J/molxK	225.59	NIST Webbook

speedsl	1152.00	m/s	308.15	Densities, Speeds of Sound, Excess Molar Volumes, and Excess Isentropic Compressibilities at T = (298.15 and 308.15) K for Methyl Methacrylate + 1-Alkanols (1-Butanol, 1-Pentanol, and 1-Heptanol) + Cyclohexane, + Benzene, + Toluene, + p-Xylene, and + Ethylbenzene
---------	---------	-----	--------	--

speedsl	1182.00	m/s	298.15	Densities, Speeds of Sound, Excess Molar Volumes, and Excess Isentropic Compressibilities at T = (298.15 and 308.15) K for Methyl Methacrylate + 1-Alkanols (1-Butanol, 1-Pentanol, and 1-Heptanol) + Cyclohexane, + Benzene, + Toluene, + p-Xylene, and + Ethylbenzene
---------	---------	-----	--------	--

speedsl	1153.00	m/s	308.15	Densities, Excess Molar Volumes at T = (298.15 to 313.15) K, Speeds of Sound, Excess Isentropic Compressibilities, Relative Permittivities and Deviations in Molar Polarizations at T = (298.15 and 308.15) K for Methyl Methacrylate + 2-Butoxyethanol or + Dibutyl Ether + Benzene, + Toluene and + p-Xylene
---------	---------	-----	--------	--

speedsl	1181.00	m/s	298.15	Densities, Excess Molar Volumes at T = (298.15 to 313.15) K, Speeds of Sound, Excess Isentropic Compressibilities, Relative Permittivities and Deviations in Molar Polarizations at T = (298.15 and 308.15) K for Methyl Methacrylate + 2-Butoxyethanol or + Dibutyl Ether + Benzene, + Toluene and + p-Xylene
---------	---------	-----	--------	--

## Correlations

Information	Value
Property code	pvap
Equation	$\ln(P_{vp}) = A + B/T + C \cdot \ln(T) + D \cdot T^2$
Coeff. A	1.28053e+02
Coeff. B	-8.95480e+03
Coeff. C	-1.71457e+01
Coeff. D	1.47176e-05
Temperature range (K), min.	224.95
Temperature range (K), max.	564.00

## Sources

Determination of Henry's Law Constants Using Internal Standards  
KDB Vapor Pressure Data:

<https://www.doi.org/10.1021/je3010535>

NIST Webbook:

<https://www.thermo.com/research/kdb/hcprop/showprop.php?cmpid=1171>

<http://webbook.nist.gov/cgi/cbook.cgi?ID=C80626&Units=SI>

Densities, speeds of sound and excess properties of (benzotrile + methyl methacrylate, or + ethyl methacrylate, or + n-butyl methacrylate) binary mixtures at temperatures from 293.15 K Phase Equilibria at High Pressures: Densities, ultrasonic speeds, excess and partial molar properties of binary mixtures of excess molar volumes and viscosity for the Methyl Methacrylate + 2-Butyl-1-methylimidazolium Hexafluorophosphate Ionic Liquid Binary System at Atmospheric Pressure:

<https://www.doi.org/10.1016/j.jct.2018.12.031>

<http://pubs.acs.org/doi/abs/10.1021/ci9903071>

<https://www.doi.org/10.1021/je049639z>

<https://www.doi.org/10.1016/j.jct.2018.03.013>

<https://www.doi.org/10.1021/je900091b>

Phase Behavior Studies of  
 2-Hydroxyethyl Methacrylate and  
 Methyl Methacrylate in Pressure  
 Carbon Dioxide, methyl methacrylate or  
 Methyl Methacrylate + Methylbutyl  
 Methacrylate, Ethyl Acrylate + Butyl  
 Acrylate, Methyl Methacrylate + Methyl  
 Methacrylate + 2-Propanol + Methyl  
 Methacrylate, Volume Fractions and  
 Deviation for the Methanol + Methyl  
 Methacrylate Binary System at T)  
 (283.15 to 333.15) K:  
 KDB:

<https://www.doi.org/10.1021/je700272y>  
<https://www.doi.org/10.1016/j.fluid.2007.07.011>  
<https://www.doi.org/10.1007/s10765-005-5571-9>  
<https://www.doi.org/10.1021/je700118q>  
<https://www.doi.org/10.1021/je800164w>  
<http://link.springer.com/article/10.1007/BF02311772>  
<https://www.thermoflow.com/files/research/kdb/mol/mol1171.mol>

Aqueous Solubility Prediction Method:

<http://onschallenge.wikispaces.com/file/view/AqueousDataset002.xlsx/351826032/AqueousDa>

Liquid liquid equilibria for the ternary  
 systems water + 1-propanol + methyl  
 methacrylate, methyl methacrylate +  
 (298.15 to 313.15) K. Speeds of Sound,  
 Excess Entropy, Compressibilities,  
 temperature on the solubility of organic  
 compounds in liquid equilibria for systems of  
 water + methanol + methyl methacrylate  
 and several temperatures  
 2-Butoxyethanol or + Dibutyl Ether +  
 Benzene, Speeds of Sound, Excess  
 Molar Volumes, and Excess Isentropic  
 Compressibilities at 0.1 MPa and  
 298.15 K for Methyl Methacrylate or  
 Methyl Methacrylate + 1-Propanol, and  
 Methyl Methacrylate + 2-Propanol, and  
 Methyl Methacrylate + Ethyl Methacrylate  
 and Methyl Methacrylate + Methyl Methacrylate  
 in Methyl Methacrylate at different  
 temperatures:

<https://www.doi.org/10.1016/j.fluid.2007.05.018>  
<https://www.doi.org/10.1021/je034022n>  
<https://www.doi.org/10.1016/j.jct.2011.11.020>  
<https://www.doi.org/10.1016/j.fluid.2011.07.008>  
[https://en.wikipedia.org/wiki/Joback\\_method](https://en.wikipedia.org/wiki/Joback_method)  
<https://www.doi.org/10.1021/je100652b>  
<https://www.doi.org/10.1021/je7002572>  
<https://www.doi.org/10.1016/j.jct.2013.01.013>  
<https://www.doi.org/10.1016/j.jct.2006.05.012>

## Legend

affp:	Proton affinity
basg:	Gas basicity
chl:	Standard liquid enthalpy of combustion
cpg:	Ideal gas heat capacity
cpl:	Liquid phase heat capacity
cps:	Solid phase heat capacity
dvisc:	Dynamic viscosity
gf:	Standard Gibbs free energy of formation
hf:	Enthalpy of formation at standard conditions
hfl:	Liquid phase enthalpy of formation at standard conditions
hfus:	Enthalpy of fusion at standard conditions
hfust:	Enthalpy of fusion at a given temperature
hsubt:	Enthalpy of sublimation at a given temperature
hvap:	Enthalpy of vaporization at standard conditions
hvapt:	Enthalpy of vaporization at a given temperature
ie:	Ionization energy
log10ws:	Log10 of Water solubility in mol/l
logp:	Octanol/Water partition coefficient
mcvol:	McGowan's characteristic volume
pc:	Critical Pressure
vpap:	Vapor pressure

<b>rho:</b>	Liquid Density
<b>rinpol:</b>	Non-polar retention indices
<b>ripol:</b>	Polar retention indices
<b>sfust:</b>	Entropy of fusion at a given temperature
<b>sl:</b>	Liquid phase molar entropy at standard conditions
<b>speedsl:</b>	Speed of sound in fluid
<b>tb:</b>	Normal Boiling Point Temperature
<b>tc:</b>	Critical Temperature
<b>tf:</b>	Normal melting (fusion) point
<b>tt:</b>	Triple Point Temperature
<b>vc:</b>	Critical Volume

Latest version available from:

<https://www.cheméo.com/cid/57-301-4/Methyl-methacrylate.pdf>

Generated by Cheméo on 2024-04-19 19:03:29.841273833 +0000 UTC m=+15842658.761851155.

Cheméo (<https://www.cheméo.com>) is the biggest free database of chemical and physical data for the process industry.