

di(Butoxyethyl)adipate

Other names:	Hexanedioic acid, bis(2-butoxyethyl) ester Adipic acid, bis(ethylene glycol monobutyl ether) ester Adipic acid, bis(2-butoxyethyl) ester Adipic acid, bis(2-butyoxyethyl) ester Adipic acid, dibutoxyethyl ester Adipol BCA Bis(ethylene glycol monobutyl ether) adipate Bis(2-butoxyethyl) adipate Butyl "Cellosolve" Adipate (BCA) Di(2-butoxyethyl) adipate Dibutyl Cellosolve Adipate Staflax DBEA Butyl "cellosolve" adipate Adipic acid, di(2-butoxyethyl) ester Hexanedioic acid, 1,6-bis(2-butoxyethyl) ester NSC 4813
Inchi:	InChI=1S/C18H34O6/c1-3-5-11-21-13-15-23-17(19)9-7-8-10-18(20)24-16-14-22-12-6-4-2
InchiKey:	IHTSDBYPAZEUOP-UHFFFAOYSA-N
Formula:	C18H34O6
SMILES:	CCCCOCCOC(=O)CCCCC(=O)OCCOCCCC
Mol. weight [g/mol]:	346.46
CAS:	141-18-4

Physical Properties

Property code	Value	Unit	Source
gf	-577.16	kJ/mol	Joback Method
hf	-1168.89	kJ/mol	Joback Method
hfus	50.33	kJ/mol	Joback Method
hvap	78.79	kJ/mol	Joback Method
log10ws	-3.26		Crippen Method
logp	3.267		Crippen Method
mcvol	291.100	ml/mol	McGowan Method
pc	1198.96	kPa	Joback Method
tb	808.66	K	Joback Method
tc	992.65	K	Joback Method
tf	481.40	K	Joback Method
vc	1.127	m3/kmol	Joback Method

Temperature Dependent Properties

Property code	Value	Unit	Temperature [K]	Source
cpg	911.35	J/mol×K	808.66	Joback Method
cpg	985.71	J/mol×K	961.99	Joback Method
cpg	972.97	J/mol×K	931.32	Joback Method
cpg	959.16	J/mol×K	900.66	Joback Method
cpg	944.28	J/mol×K	869.99	Joback Method
cpg	928.34	J/mol×K	839.33	Joback Method
cpg	997.37	J/mol×K	992.65	Joback Method
dvisc	0.0000399	Pa×s	808.66	Joback Method
dvisc	0.0000521	Pa×s	754.12	Joback Method
dvisc	0.0000709	Pa×s	699.57	Joback Method
dvisc	0.0001018	Pa×s	645.03	Joback Method
dvisc	0.0001561	Pa×s	590.49	Joback Method
dvisc	0.0002611	Pa×s	535.94	Joback Method
dvisc	0.0004909	Pa×s	481.40	Joback Method

Sources

NIST Webbook:	http://webbook.nist.gov/cgi/cbook.cgi?ID=C141184&Units=SI
Crippen Method:	http://pubs.acs.org/doi/abs/10.1021/ci990307l
Crippen Method:	https://www.chemeo.com/doc/models/crippen_log10ws
Joback Method:	https://en.wikipedia.org/wiki/Joback_method
McGowan Method:	http://link.springer.com/article/10.1007/BF02311772

Legend

cpg:	Ideal gas heat capacity
dvisc:	Dynamic viscosity
gf:	Standard Gibbs free energy of formation
hf:	Enthalpy of formation at standard conditions
hfus:	Enthalpy of fusion at standard conditions
hvap:	Enthalpy of vaporization at standard conditions

log10ws:	Log10 of Water solubility in mol/l
logp:	Octanol/Water partition coefficient
mcvol:	McGowan's characteristic volume
pc:	Critical Pressure
tb:	Normal Boiling Point Temperature
tc:	Critical Temperature
tf:	Normal melting (fusion) point
vc:	Critical Volume

Latest version available from:

<https://www.cheméo.com/cid/88-971-7/di-Butoxyethyl-adipate.pdf>

Generated by Cheméo on 2025-12-21 21:22:53.968384099 +0000 UTC m=+6100371.498424763.

Cheméo (<https://www.cheméo.com>) is the biggest free database of chemical and physical data for the process industry.